

BERMUDA ROOFING MORTAR

1 of 3

PRODUCT DESCRIPTION

Kaidisen™ Bermuda Roofing Slate Mortar is a light weight mortar engineered specifically to provide optimal bond and structural capabilities in the **Kaidisen™ Bermuda Roofing System**.

RECOMMENDED USE

Kaidisen™ Bermuda Roofing Mortar is the primary component bonding **Kaidisen™ Bermuda Roofing Slate** to form the **Kaidisen™ Bermuda Roofing System**.

APPEARANCE

Grey

TECHNICAL DATA

Minimum Compressive Strength	840 psi (5.79 MPa)
Modulus of Elasticity	368,000 psi (2,537 MPa)
Flexural Tensile Strength	65 psi 108.4 MPa
Thermal Conductivity	0.97 BTU per in /ft2 / hr per deg F 0.14 W/mK
Thermal Resistance	R 1.03 per inch 7.14 mK/W
Linear Coefficient of Thermal Expansion	4.5×10^{-6} 1° F (8.1×10^{-6} ° C)
Design Density ⁽¹⁾	55 pcf (720 kg/m ³)
Nominal Dry Density	53 pcf (600 kg/m ³)
Moisture Content	(Average) 3% (by mass)
Vapor Permeance	30 perms

INSTALLATION

General

Bermuda Roofing Slates are laid in a shingle fashion up the roof forming courses parallel to the eave with 9 inch exposures. Each Bermuda Roofing Slate is fully supported on a 1 inch thick bed of Kaidisen Mortar giving each successive course a cross sectional profile of approximately 2 inches thick. Mortar is molded to cover the exposed butt end of the Bermuda Roofing Slate forming a canted edge, a feature typical of an authentic Bermuda roof called the weather.

Set the standard for smoothness early in the project with a mock-up at ground level or in-place.

Set each successive course in a full bed of mortar (approximately 1 inch thick). .Employ the following Sequence of installation on steep sloped installation:

Prepare Bermuda Roofing Slate by cleaning them a hose as they are unpacked removing particles. This will also soak them thoroughly to produce a Saturated Surface Dry (SSD) condition which is required before installing them.

BERMUDA ROOFING MORTAR

2 of 3

Mix mortar by machine mixer or drill in bucket making only enough mortar that will be used within one hour. Mix 1 bag (1.1 CF) with approximately 3.5 gallons of clean potable water depending on the weather conditions and the temperature. Do not retemper mortar once it is begun to set up.

Smear mortar onto the new mating surface of each Bermuda Roofing Slate covering the concealed portion of each course working the mortar into the surface.

Place mortar to form bed on upper half of Bermuda Roofing Slate to be covered. Finished bed once next Bermuda Roofing Slate is set shall be $\frac{3}{4}$ inch to 1 inch thick.

Embed reinforcing mesh into the smeared mortar allowing the mesh to overhang the top of the Bermuda Roofing Slate extending up the roof to the next batten. Staple the top edge of the mesh to the batten to prevent mortar from pushing the mesh down into the cavity.

Back-butter each Bermuda Roofing Slate with fresh mortar coating the lower mating surface and sides just before laying it into the mortar bed.

Apply mortar bed to upper half of Bermuda Roofing Slate below and set Bermuda Roofing Slate aligning it with the top of the next batten. Seat Bermuda Roofing Slates in mortar bed by moving them from side to side as they are pressed into the bed.

Lay each Bermuda Roofing Slate with its upper edge directly over the top edge of its supporting batten ensuring full support of each Bermuda Roofing Slate by the battens.

If one edge of the Bermuda Roofing Slate is chipped or out of square, place the factory finished or still square edge on the batten leaving the broken end to rest on the mortar bed over the Bermuda Roofing Slate below. This ensures the Bermuda Roofing Slate will be firmly and fully supported by the batten. Fill in with mortar to compensate for the missing AAC.

Allow a minimum head joint width of $\frac{3}{16}$ inch between laterally adjacent Bermuda Roofing Slates when seating the Bermuda Roofing Slate in to the bed joint and ensure head joints are fully packed with mortar.

After embedding the Bermuda Roofing Slate into the mortar bed insert a Kaidisen clip over the upper edge of each Bermuda Roofing Slate. (If enhanced uplift requirements are indicated follow schedule provided on drawing). NOTE: Typically the field of the roof will require one clip per Bermuda Roofing Slate; edges and ridges may require additional clips or screws.

BERMUDA ROOFING MORTAR

3 of 3

Apply mortar to butts of AAC units and strike smooth with a trowel to form a fillet fully sealing off the butt end to form the traditional feature of the Bermuda Roof known as “The Weather”.

Smooth the exposed mortar of the “The Weather” with a steel trowel sealing surface with cement paste brought to the surface by the action of the trowel.

Keep cavities clean of mortar droppings and other materials during construction.

Stopping and Resuming Work: Rack back units; do not tooth. Do not retemper mortar with water once it has begun to set up. When resuming work ensure mating surfaces of Bermuda Roofing Slates and starters receiving fresh mortar are SSD.

Clean masonry as work progresses. Remove mortar fins and smears wherever possible before tooling joints.

As the mortar sets, finish exposed mortar surfaces, smooth to achieve an even appearance. After mortar has set, grind or cut away rough edges fins and other protrusions from the surface using trowels and rasps to achieve a visually smooth surface.

For more information about the Kaidisen Bermuda Roofing System and how it is constructed refer to our other data sheets and our guide specification.